

---

## Overview

This standard covers a broad range of basic semi-automatic MIG, MAG or flux cored-wire arc welding equipment competences that will prepare you for entry into the engineering or manufacturing sectors, creating a progression between education and employment, or that will provide a basis for the development of additional skills and occupational competences in the working environment.

You will be expected to prepare the welding equipment and to ensure that all leads/cables, shielding gas system, hoses and wire feed mechanisms are securely connected and free from damage. You will also need to obtain and check that all the workholding equipment is in a safe and usable condition.

In preparing to weld, you will need to set and adjust the welding conditions, in line with instructions and/or the welding procedure specification. You must operate the equipment safely and correctly, and make any necessary adjustments to settings in line with your permitted authority, in order to produce the welded joints to the required specification.

On completion of the welding operations, you will be expected to check the quality of the welds using measuring equipment, visual examination and destructive testing techniques, as appropriate to the aspects being checked. You will need to be able to recognise welding defects, to take appropriate action to limit any faults that occur and to ensure that the finished workpiece is within the specification requirements. On completion of the welding activities, you will be expected to return all tools, equipment and workholding devices to their designated location, and to leave the welding equipment and work area in a safe and tidy condition.

Your responsibilities will require you to comply with health and safety requirements and organisational policy and procedures for the welding activities undertaken. You will need to take account of any potential difficulties or problems that may arise with the welding activities, and to seek appropriate help and advice in determining and implementing a suitable solution. You will work under a high level of supervision, whilst taking responsibility for your own actions and for the quality and accuracy of the work that you carry out.

Your underpinning knowledge will provide an understanding of your work, and will enable you to apply appropriate semi-automatic MIG, MAG or flux cored-wire welding techniques safely. You will understand the welding process, and its application, and will know about the equipment, materials and consumables, to the required depth to provide a sound basis for carrying out the activities to the required specification. You will understand the safety precautions required when working with the MIG, MAG or flux cored-wire welding equipment, and with the associated tools and equipment. You will be required to demonstrate safe working practices throughout, and will understand the responsibility you owe to yourself and others in the workplace.

---

### **Specific Standard Requirements**

Welded joints must be at least 150mm long, using single or multi-run welds (as appropriate), with at least one stop and start included.

---

## Performance criteria

### You must be able to:

1. work safely at all times, complying with health and safety legislation, regulations, directives and other relevant guidelines
2. plan the welding activities before you start them
3. obtain and prepare the appropriate welding equipment and welding consumables
4. prepare and support the joint, using the appropriate methods
5. tack weld the joint at appropriate intervals, and check the joint for accuracy before final welding
6. weld the joint to the specified quality, dimensions and profile
7. use appropriate methods and equipment to check the quality, and that all dimensional and geometrical aspects of the weld are to the specification
8. deal promptly and effectively with problems within your control, and seek help and guidance from the relevant people if you have problems that you cannot resolve
9. shut down and make safe the welding equipment on completion of the welding activities

## Knowledge and understanding

### You need to know and understand:

1. the safe working practices and procedures to be followed when preparing and using MIG, MAG or flux cored wire arc welding equipment (such as general workshop safety; appropriate personal protective equipment (PPE); fire prevention; protecting other workers from the effects of the welding arc; safety in enclosed/confined spaces; fume extraction/control)
2. the hazards associated with MIG, MAG or flux cored-wire arc welding (such as live electrical components; poor earthing; the electric arc; fumes and gases; spatter; hot slag and metal; grinding and mechanical metal/slag removal; elevated working; enclosed spaces; slips, trips and falls), and how they can be minimised
3. the personal protective equipment to be worn for the welding activities (such as correctly fitting overalls; leather aprons, welding gloves/gauntlets; safety boots; head/eye shield with correct shade of filter)
4. the correct handling and storage of gas cylinders (such as manual handling and use of cylinder trolley, leak detection procedures, relevant BCGA codes of practice, cylinder identification, gas pressures, cylinder and equipment safety features)
5. how to use and extract information from engineering drawings and related specifications (to include symbols and conventions to appropriate BS or ISO standards) in relation to work undertaken
6. the semi-automatic MIG, MAG or flux cored wire arc welding process (such as basic principles of fusion welding, power sources, the major parts of the welding equipment and their function)
7. types, selection and application of electrode wires (such as solid and cored)
8. reasons for using shielding gases, and the types and application of the various gases
9. gas pressures and flow rates (in relation to the type of material being welded)
10. the types of welded joints to be produced (such as lap joints, corner joints, tee joints and butt welds)
11. terminology used for the appropriate welding positions
12. how to prepare the materials in readiness for the welding activity (such as ensuring that the material is free from excessive surface contamination - such as rust, scale, paint, oil/grease and moisture; ensuring edges to be welded are correctly prepared - such as made flat, square or bevelled)
13. how to set up and restrain the joint, and the tools and techniques to be used (such as the use of jigs and fixtures, restraining devices - such as clamps and weights/blocks; setting up the joint in the correct position and alignment)
14. tack welding size and spacing (in relation to material thickness)

15. checks to be made prior to welding (such as confirming the correct set-up of the joint; the condition of electrical connections, welding return and earthing arrangements; wire feed mechanisms; gas supply; operating parameters)
16. the techniques of operating the welding equipment to produce a range of joints in the various joint positions (such as fine adjustment of parameters; correct manipulation of the welding gun; blending in stops/starts and tack welds)
17. methods/modes of metal transfer and their uses (such as dip, globular, free flight, spray and pulsed)
18. how to close down the welding equipment safely and correctly
19. how to control distortion (such as welding sequence; deposition technique)
20. problems that can occur with the welding activities (such as causes of distortion and methods of control; effects of welding on materials and sources of weld defects), and how these can be overcome
21. the safe working practices and procedures to be adopted when preparing the welds for examination (such as handling hot materials, using chemicals for cleaning and etching, using equipment to fracture welds)
22. how to prepare the welds for examination (such as removing surface irregularities; cleaning the weld, polishing and making saw cuts on welds to be break tested)
23. how to check the welded joints for uniformity, alignment, position, weld size and profile
24. the various procedures for visual examination of the welds for cracks, porosity and slag inclusions (such as dye penetrant, fluorescent penetrant; magnetic particle testing)
25. the various procedures for carrying out destructive tests on the welds (such as macroscopic examination, bend tests, nick break tests)
26. methods of removing a specimen of weld from a suitable position in the joint (such as a stop/start position), using a non thermal process (such as hand saws, power saws, abrasive discs)
27. how to examine the welds after the tests, and how to check for such defects as the degree of penetration and fusion, inclusions, porosity, cracks, undercut and overlap, uneven and irregular ripple formation
28. when to act on your own initiative and when to seek help and advice from others
29. the importance of leaving the work area and equipment in a safe condition on completion of the welding activities (such as isolation of electrical supplies; safely storing welding cables and electrode holders; storing electrodes; removing and disposing of waste)

---

### Scope/range related to performance criteria

1. Prepare for the MIG, MAG or flux cored-wire arc welding process by carrying out **all** of the following:
  1. adhere to procedures or systems in place for risk assessment, COSHH, personal protective equipment (PPE) and other relevant safety regulations
  2. check the condition of, and correctly connect, welding leads/cables, hoses, shielding gas supply and wire feed mechanisms
  3. set and adjust the welding conditions/parameters, in accordance with the welding procedure specification
  4. prepare the work area for the welding activities (such as positioning welding screens and fume extraction)
  5. prepare the materials and joint in readiness for welding (such as cleaning of joint faces, grinding weld preparations, setting up the joint, supporting the joint)
  6. make sure the work area is maintained and left in a safe and tidy condition
2. Use manual/semi-automatic welding and related equipment to include **one** of the following:
  1. MIG
  2. MAG
  3. Flux cored wire welding equipment
3. Use consumables appropriate to the material and application, to include: **one** of the following wire types:
  1. solid wire
  2. cored wire

Plus **one** of the following types of shielding gas:

  3. inert
  4. active
4. Produce **three** of the following welded joints of at least 150mm long, by single or multi-run (as appropriate), with at least one stop and start included:
  1. fillet lap joints
  2. corner joints
  3. Tee fillet joints
  4. butt joints

5. Produce joints as follows: **one** type of material from the following:

1. carbon steel
2. stainless steel
3. aluminium

And **two** forms of material from the following:

4. plate
5. sheet (less than 3mm)
6. pipe/tube
7. section
8. other specific forms

6. Weld joints in good access situations in **two** of the following BS EN ISO 6947 positions:

1. Flat (PA)
2. Vertical upwards (PF)
3. Horizontal vertical (PB)
4. Vertical downwards (PG)
5. Horizontal (PC)

7. Check that the welded joint conforms to the specification, by checking **all** of the following:

1. dimensional accuracy
2. size and profile of weld
3. number of runs
4. alignment/squareness

8. Carry out non-destructive testing of the welds, using **one** of the following:

1. dye penetrant
2. fluorescent penetrant
3. magnetic particle

9. Carry out destructive tests on weld specimens using **one** of the following:

1. macroscopic examination
2. nick break test
3. bend tests (such as face, root or side, as appropriate)

10. Identify **all** of the following weld defects:

1. lack of continuity of the weld
2. uneven and irregular ripple formation
3. incorrect weld size or profile

Plus **four** more of the following:

4. undercutting
5. internal cracks
6. overlap
7. surface cracks
8. inclusions
9. lack of fusion
10. porosity
11. lack of penetration

11. Produce welded joints which meet **all** of the following (with reference to BS 4872 Part 1 Weld test requirements):

1. welds meet the required dimensional accuracy
2. fillet welds are equal in leg length and slightly convex in profile, with the size of the fillet equivalent to the thickness of the material welded
3. the weld contour is linear, of uniform profile, free from excessive undulations, with regular and even ripple
4. the welds are adequately fused, and there is minimal undercut, overlap and surface inclusions
5. weld finishes are built up to the full section of the weld
6. joins at stop/start positions merge smoothly, with no pronounced hump or crater in the weld surface
7. tack welds are blended in to form part of the finished weld, without excessive hump
8. corner joints have minimal burn through to the underside of the joint or, where appropriate, penetration is present to a maximum depth of 3mm for at least 75% of the joint
9. the weld surface is free from cracks, and substantially free from porosity, shrinkage cavities and trapped slag
10. the weld surface and adjacent parent metal is substantially free from arcing or chipping marks



---

## Behaviours

# Additional Information

You will be able to apply the appropriate behaviours required in the workplace to meet the job profile and overall company objectives, such as:

- strong work ethic
- positive attitude
- team player
- dependability
- responsibility
- honesty
- integrity
- motivation
- commitment

Developed by	Enginuity
Version Number	3
Date Approved	30 Mar 2017
Indicative Review Date	31 Mar 2020
Validity	Current
Status	Original
Originating Organisation	Semta
Original URN	SEMPEO2-29
Relevant Occupations	Engineering, Engineering and Manufacturing Technologies
Suite	Performing Engineering Operations Suite 2
Keywords	engineering; engineering operations; semi-automatic MIG welding equipment; semi-automatic MAG welding equipment; continuous wire welding equipment; flux cored-wire arc welding equipment; manufacturing; shielding gas system; hoses; wire feed mechanisms